


Table 2
Classification of pedestrian surface materials according to the AS 4586: 2013 Wet
Pendulum Test

Class	Pendulum SRV	
	Slider 96	Slider 55
P5	>54	>44
P4	45 – 54	40 – 44
P3	35 – 44	35 – 39
P2	25 – 34	20 – 34
P1	12 – 24	<20
P0	<12	

Note:

It is expected that these surfaces will have greater slip resistance when dry.
AS/NZS 3661.1:1993 requires that when tested wet the pedestrian surface shall have a mean coefficient of friction of not less than 0.4 and no specimen in that sample shall be less than 0.35
As per New Zealand Department of Building and Housing Code wet access route required at least a 0.4 pass

Report Issued By: Maciek Gaworecki on 08/11/2019

Checked By: 

Disclaimer: These test results apply to the samples as received by the Laboratory. Testing does not take into account any future wear or maintenance of the surface. No liability will be accepted by the Laboratory for any misrepresentation with respect to the testing and/or the use of these test results.